

Amendments to the Claims

This listing of the claims will serve to replace all prior versions, and listings, of claims in the application:

Listing of Claims:

--1. (Currently amended) A production method for an aluminum alloy coated steel sheet, comprising dipping a base steel sheet into a coating bath of an Al-Si-Cr-Mg bath composition [with] consisting essentially of a Si content of 7 to 15 parts by weight, a Cr content of 0.5 to 1.5 parts by weight and a Mg content of 0.46 to 3.0 parts by weight.

2. (Original) The production method as set forth in claim 1, wherein an adhesion quantity of coating is 20 to 300 g/m² on a one surface basis.

3. (Original) The production method as set forth in claim 1, wherein the bathing temperature of the base steel sheet is 650 to 700 °C.

4. (Original) The production method as set forth in claim 2, wherein the bathing temperature of the base steel sheet is 650 to 700 °C.--